

MINERAL DECORATIVE FINISHING MORTARS

data sheet 13

700
MINERAL STRUCTURAL DECORATIVE FINISHING MORTAR COLOURED

700 NW

MINERAL STRUCTURAL DECORATIVE FINISHING MORTAR
NATURAL WHITE

700 EW

MINERAL STRUCTURAL DECORATIVE FINISHING MORTAR
EXTRA WHITE

Description and field of use:

Factory-prepared mortar for final layer,raw-white or extra white, as well as in colors in color charts for facade surfaces or interior surfaces, on base mortars or previously processed surfaces or building boards.


Composition:

- whitewash
- white cement
- gypsum (Milfas 351)
- fine white calcareous sand
- additives
- oxide paint

Properties:

- ecologically advisable
- high permeability
- good adhesion
- good repellence
- high durability

broad capabilities to achieve the desired decorative appearance smooth, drawn or corroded structures



Surface preparation:

Surface has to be clean without frost, loose parts and cracks.

Material preparation and processing:

Pour 0,24l of water/1 kg of dry mass in a clean container, mix manually or mechanically and progressively add the powder. Mix until the mass becomes homogenous, without lumps. Leave the mass for 5-10 minutes, mix again and it is ready for use. While working mix the mass to avoid depositig of granular grains. Apply with metal trowel as thick as the largest grain in the mass, then rub, draw and scrub to achieve the desired structure. Apply continually from the edge to the edge of the wall.

Processing conditions:

The temperature of surface and air should be between 5 and 30 C. Surfaces directly exposed to sun or strong wind should be protected with protective curtain.

Consumption:

1,2 mm: 2,5 kg/m2 1,5 mm: 2,7 kg/m2 2,0 mm: 3,0 kg/m2 3,0 mm: 4,0 kg/m2

Packaging:


25 kg bag

Storage:

Storable for 6 months in original packaging on wooden grate in dry place.

Safety warning:

Irritant. Protect skin, mucous membrane and eyes.





MIII EVI d.o.o. Kreševo, BiH

Technical instructions provided in this publication are based on our experience and are provided in order to achieve the optimal results in using this product. For damages caused by wrong choice of product, its irregular application or low quality work we do not accept responsibility. This data sheet complements and replaces all previous editions. Milicevic Ltd. Kresevo reserves the right to all subsequent changes and additions.