

GYPSUM LIME PLASTER

data sheet 4

150 BASIC GYPSUM PLASTER SKIMMED

> 190 BASIC GYPSUM PLASTER FELT

Description and field of use:

Finished basic skimmed (Milfas 150) or the felt (Milfas 190) mortar for interior walls and ceilings in all normal surfaces (brick, brick blocks, cement blocks, stone, textured concrete, etc.).

Composition:

- gypsum
- lime
- Limestone grain 1mm
- filer
- additives

Properties:

- Good mechanical and manual processing
- high abundance
- regulates humidity

Surface preparation:

The substrate must be clean, dust free, rough and tough enough before applying mortar. Before applying the plaster impregnate highly absorbing surfaces with MILFAS Acrylic Primers (Grund).

♦ milfas

Material preparation and processing:

Mix the content of the bag with cca 111 of clean water until reaching a homogenous mass. The obtained mixture is applied manually or mechanically to the required thickness, with stirring during operation. Minimum thickness for the walls is 10 mm, while for ceilings 7 mm. Level the surface with approximately 2 m long H rod, and smoothen with sander. When applied mass dries it is necessary to moisten it with water and felt with rough sponge board, and then skim (for Milfas 150). Mortar should be applied to the concrete surface at least 3 months old. Finishing is possible after 21 day.

Processing conditions:

During processing and subsequent drying ambient temperature and the surface should not be lower than +5 °C. Protect from freezing, rapid drying due direct sunlight and rain exposure.

Consumption:

Cca12kg/m for layer thk=10mm.

Packaging:

30 kg bag

Storage:

Storable for 6 months in original packaging on wooden grate in dry place.

Safety warning:

Irritant. Protect skin, mucous membrane and eyes.



mili evi d.o.o. Kreševo, BiH

Technical instructions provided in this publication are based on our experience and are provided in order to achieve the optimal results in using this product. For damages caused by wrong choice of product, its irregular application or low quality work we do not accept responsibility. This data sheet complements and replaces all previous editions. Milicevic Ltd. Kresevo reserves the right to all subsequent changes and additions.